

METALPLATE PLUS

**Non-Oxidizing Metallic Aggregate
Dry Shake Floor Hardener**



1. Product Description

a. Basic Use: Metalplate Plus is intended for use as a dry shake surface hardener on fresh concrete to provide substantially greater wear resistance on the surface of industrial grade floor slabs in combination with 100% resistance to oxidation or rusting. It is applied to the surface of fresh concrete during the normal finishing operations on the floor with standard finishing equipment

b. Features/Benefits:

- Provides a high strength floor surface for superior wear resistance.
- Formulated with non-oxidizing metallic aggregate which gives up to 8 times the wear resistance of plain concrete floors.
- Suitable for both interior and exterior slabs.
- Works into the surface of fresh concrete easily for complete, monolithic integration.
- Zero absorption aggregate densifies the floor surface for better resistance to water, fluid, and oil spills.
- Resistant to de-icing salts.
- Hard, non-dusting surface makes floor cleaning and maintenance easier and faster.
- Outwears conventional natural aggregate dry shake floor hardeners by up to 400%.

c. Typical Applications: Warehouses of all types, loading docks, manufacturing plants, terminals, processing plants, metal shops, steel mills, automotive plants and print shops.

d. Limitations: Metalplate Plus should not be used in areas subject to acid spillage or other chemicals which attack portland cement.

e. Composition: Metalplate Plus is a blend of a specially designed non-oxidizing metallic aggregate, a portland cement binder, and a proprietary chemical system.

f. Color/Appearance: Metalplate Plus provides a gray floor color when used as a natural colored, unpigmented system. It is also available in standard colors including light reflective, french gray, battleship gray, black, brown, tile red, terra cotta, and green.

Metalcrete Industries

2. Packaging

Metalplate Plus is packaged in 50-lb. (22.7 kg) moisture resistant bags, 60 bags per pallet. Shelf life is 18 months with proper storage and protection.

3. Estimating/Coverage

Metalplate Plus has a normal usage rate of 0.75 to 2.00 psf (3.7 to 9.8 kg/sq. m). The following table may be used for coverage:

Coverage Per Bag	Application Rate
67 sq. ft. (6.2 sq. m)	0.75 psf (3.7 Kg/sq. m)
50 sq. ft. (4.6 sq. m)	1.00 psf (4.9 Kg/sq. m)
40 sq. ft. (3.7 sq. m)	1.25 psf (6.1 Kg/sq. m)
33 sq. ft. (3.1 sq. m)	1.50 psf (7.3 Kg/sq. m)
25 sq. ft. (2.3 sq. m)	2.00 psf (9.8 Kg/sq. m)

4. Technical Data

- a. Applicable Standards:**
- ACI 302.1R-89, Guide for Concrete Floor and Slab Construction.
 - ASTM C 779, Standard Test Method for Abrasion Resistance of Horizontal Concrete Surfaces.
- b. Compressive Strength:** ASTM C 109, 2 in. (50 mm) cubes.

Age	Strength
1 day	5,200 psi (35.9 MPa)
3 days	8,100 psi (55.9 MPa)
7 days	9,900 psi (68.3 MPa)
28 days	11,400 psi (78.6 MPa)

c. Wear Resistance: ASTM C 779, Procedure A: 0.014 in. (0.35 mm) at 60 minutes.

5. Directions for Use

(Follow basic ACI 302 guidelines)

a. Preparation: Subgrade should be well compacted and graded to proper elevation. If a vapor barrier is used, it should not be placed over the subgrade but rather a minimum of 3 in. (76 mm) under the compacted fill. Vapor barriers will aggravate finishing problems and can contribute to slab curling. Forms should be set strong and true. Strip placements are preferred over checkerboarding. Place under roof whenever possible.

4133 Payne Avenue • Cleveland, Ohio 44103
440-526-5600 • 800-526-5602 • FAX 440-526-5601



b. Concrete: Concrete mix must be non-air-entrained and not contain any calcium chloride based admixtures. Concrete must contain enough water to properly wet out the dry shake under the job site conditions, normally at 3-1/2 in. (89 mm) to 4-1/2 in. (115 mm) slump without considering the influence of admixtures. Place the concrete and screed into place, flush with the top of form. Bull float to smooth surface and fill low spots. (Note: On floors where tight tolerances are required or where the tolerance is specified by "F" numbers, a check rod or highway straightedge may be desirable in lieu of bull floating. See ACI 302, Section 7.15).

c. Shake Application: Ideal shake application should take place after the initial floating of the base concrete using a power trowel with float shoes. However, other site conditions such as no roof, wind, low relative humidity and/or low concrete water content may dictate earlier application. Apply Waterhoid to help prevent rapid moisture loss. Each bay of the placement should have the proper number of bags pre-placed along the slab for accurate coverage. Remove any significant free standing bleed water with a dragged rubber hose prior to shake application. Apply 2/3 of the total shake evenly and uniformly over the slab surface. Mechanical spreader application is preferred but hand or shovel methods can also be effective. Float the shake into the slab surface after it has wetted out. Follow immediately with the remaining 1/3 of the shake and repeat the procedure.

d. Finishing: Once the shake is applied and integrated, normal floating and troweling operations can proceed as the slab sets. The best floor surface is achieved with a burnish trowel. However, colored shake floors should be finished just short of a burnish trowel to prevent discoloration from blade friction. Apply as many trowel cycles as necessary to get desired finish.

e. Curing and Sealing: Curing and sealing are very important to assure proper hydration and surface strength as well as adequate protection from the environment. Apply Seal N Kure 30 at 400 sq. ft. per gal. (9.8 sq. m/liter) using a power sprayer or roller. Use two coats for exterior exposure or extremely severe drying conditions.

Metacrete technical service representatives are available to provide on-site assistance with a minimum three day notice.

8. Technical Service

Metacrete Plus is manufactured in strict accordance with the quality control standards of Metacrete Industries. It is guaranteed to perform as indicated on this data sheet when applied by competent applicators.

7. Warranty

Metacrete Plus is normally available immediately from your local distributor or it will be shipped within 5 working days upon receipt of order. Please contact your local Metacrete representative or call Metacrete directly for more information.

6. Availability

f. Joints: Contraction joints are normally sawcut into the floor to a depth of 1/4 of the slab thickness for crack control. Construction joints are a natural consequence of the forming operation. Both types should be filled with Jointfill 302 epoxy after a minimum 3 month wait (according to ACI 302, Sect. 4.10). Isolation joints and expansion joints (around column blockouts and at walls, for example) should be filled with Vulcanox urethane to allow adequate movement.

g. User Precautions: Dry shake applications can generate free, airborne dust. Wear protective dust masks. Metacrete Plus contains portland cement. Gloves should be worn during application to prevent cement burns and skin irritation.

h. Maintenance: Metacrete Plus is intended to be free of maintenance once properly installed. Metacrete Plus floors should be cleaned with standard high alkaline floor cleaners and power scrubbers. Additional applications of Seal N Kure 30 at project turnover or at other intervals once the floor is in use are optional, but not mandatory.